



Title: VOC Emissions Test Results

Material: Wood Wool

Testing Standard: CDPH Standard Method V1.2-2017

About This Test: This test identifies volatile organic compounds (VOCs), such as formaldehyde, released into the air by products. Samples are put into an environmental chamber and the air is tested at 11-, 12- and 14-days. VOC levels are then used to predict office and school room concentrations and then compared to maximum allowable levels.

Test Result Summary:

MODELING SCENARIO	RESULT (PASS/FAIL)	TVOC (mg m <sup>-3</sup> )
Private Office (PO)	PASS	0.1
School Classroom (SC)	PASS	< 0.1

Test Date: 9/28/2018

Test ID: 103632425GRR-003b

---

**MATERIAL LOGIQ TESTING DISCLAIMER**

MATERIAL LOGIQ makes every effort to ensure the accuracy and reliability of the information provided. Laboratory testing is conducted by independent testing organizations. MATERIAL LOGIQ does not guarantee that field tests or independent tests will not vary. ASI is the parent company of MATERIAL LOGIQ and is listed as the Manufacturer within the test report. The product referenced within the test report is the same MATERIAL LOGIQ product listed on this test coversheet.

# ASI TEST REPORT

**SCOPE OF WORK**

Standard Method Version 1.2 for CDPH 01350 on Cementitious Wood Fiber Board

**REPORT NUMBER**

103632425GRR-003b

**ISSUE DATE**

30-October-2018

**PAGES**

13

**DOCUMENT CONTROL NUMBER**

Per GFT-OP-10 (6-March-2017)

© 2018 INTERTEK



## TEST REPORT FOR ASI

Report No.: 103632425GRR-003b

Date: 30-October-2018

P.O.: 00065831

Telephone: +1 616 656 7401

Facsimile: +1 616 656 2022

www.intertek.com

## SECTION 1

### CLIENT INFORMATION

Attention: Conor Cook


ASI

123 Columbia Court N

Chaska, MN 55318

Phone: (952) 466-8261

Email: [ccook@acousticalsurfaces.com](mailto:ccook@acousticalsurfaces.com)



**Amanda Tongen**  
Project Engineer



**Jesse Ondersma, Ph.D.**  
Project Reviewer

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

## SECTION 2

### SUMMARY AND CONCLUSION

Test Method: Standard Method Version 1.2 for CDPH 01350  
Modeling Scenario: Private office (PO) and school classroom (SC)  
Method Deviations: Testing performed without deviation unless noted below. The acetaldehyde blank was above  $2.0 \mu\text{g m}^{-3}$ . There is not expected to be an effect on testing.

### DESCRIPTION OF SAMPLES

Manufacturer / Location  
Product Name Cementitious Wood Fiber Board  
Product Number Not Specified  
Date of Manufacture 25-September-2018  
Date of Collection 25-September-2018  
Date of Shipment 25-September-2018  
Date Received by Lab 27-September-2018  
Date of Test Start and Duration 28-September-2018 / 336 hours  
As Received Sample Condition Good Condition  
Lab Sample ID GRR1809270014

### WORK REQUESTED/APPLICABLE DOCUMENTS

VOC Emissions Analysis: CDPH Standard Method v1.2  
Intertek Quote: Qu-00901125 and Qu-00919901

### TEST RESULTS

MODELING SCENARIO	RESULT (PASS/FAIL)	TVOC ( $\text{mg m}^{-3}$ )
Private Office (PO)	PASS	0.1
School Classroom (SC)	PASS	< 0.1

### SAMPLE DISPOSITION

At the completion of testing, samples were disposed of in a routine manner.

### SECTION 3

#### CDPH STANDARD METHOD V1.2

Date Received: 27-September-2018  
Dates Tested: 28-September-2018 to 12-October-2018

#### DESCRIPTION OF SAMPLES:

Part Description: Acoustical Panel for Absorption  
Material Submitted: Four (4) Wood and Cement Panels

#### ACCEPTANCE CRITERIA:

Referencing: CDPH Standard Method v1.2, Table 4.1  
LEED v4 - Low Emitting Materials  
LEED v4 - TVOC Ranges:  $\leq 0.5 \text{ mg m}^{-3}$   
 $0.5 \text{ to } 5.0 \text{ mg m}^{-3}$   
 $\geq 5.0 \text{ mg m}^{-3}$

#### TEST NOTES OR DEVIATIONS:

Testing performed without deviation unless noted below.

#### TEST SUMMARY:

The emissions testing was performed according to "Standard Method for the Evaluation of Volatile Organic Chemical Emissions from Indoor Sources using Environmental Chambers Version 1.2". A photograph of the tested sample is included herein. The sample was cut to an appropriate size to achieve the desired loading factor. The edges were sealed with aluminized tape. The sample was placed in conditioning in the chamber for 10 days with top and bottom surfaces exposed, before testing was initiated. Air samples were collected prior to the sample being placed in the test chamber (0 hours) and at 264, 288, and 336 hours after placement in the test chamber. Samples analyzed for individual VOCs and TVOC were collected on multi-sorbent tubes containing glass wool, Tenax TA 35/60 and Carbograph 5 TD 40/60. These VOC samples were analyzed by thermal desorption-gas chromatography/mass-spectrometry, TD-GC/MS. TVOC was calculated through integration of the chromatogram from n-pentane through n-heptadecane using toluene as a surrogate. Individual VOCs were calculated using calibration curves based on pure standards unless otherwise noted. Samples analyzed for low molecular weight aldehydes were collected on cartridges treated with 2,4-dinitrophenylhydrazine (DNPH). Low molecular weight aldehydes were analyzed using high performance liquid chromatography, HPLC.

**RESULTS:**

**Table 1: Sample and Chamber Conditions during Test Period**

PARAMETER		SYMBOL	VALUE	UNITS
Sample Dimensions	Length	-	0.246	m
	Width	-	0.250	m
	Thickness	-	-	m
Exposed Sample Surface Area		<i>A</i>	0.062	m <sup>2</sup>
Chamber Volume		<i>V</i>	0.116	m <sup>3</sup>
Chamber Loading Factor		<i>L</i>	0.53	m <sup>2</sup> m <sup>-3</sup>
Inlet Air Flow Rate		<i>Q</i>	0.116	m <sup>3</sup> h <sup>-1</sup>
Air Change Rate		<i>N<sub>ACH</sub></i>	1.00	h <sup>-1</sup>
Area Specific Flow Rate		<i>q<sub>A</sub></i>	1.88	m h <sup>-1</sup>
Chamber Pressure (Range)		<i>P</i>	18.1 (16.4-20.8)	Pa
Average Temperature (Range)		<i>T</i>	23.0 (22.9-23.1)	°C
Average Humidity (Range)		RH	50.0 (47.9-51.4)	% RH
Testing Duration		<i>t</i>	336	h

**Table 2: Test chamber background VOC concentrations in µg m<sup>-3</sup>.**

COMPOUND	CAS No.	<i>C<sub>0</sub></i>
Formaldehyde	50-00-0	0.8
TVOC	-	4.0

**Table 3: Test chamber TVOC and formaldehyde concentrations in µg m<sup>-3</sup>.**

COMPOUND	CAS No.	264 H	288 H	336 H
Formaldehyde	50-00-0	1.6	1.3	1.7
TVOC	-	30.3	26.3	28.0

**Table 4: Test chamber TVOC and formaldehyde emission factors in µg m<sup>-2</sup> h<sup>-1</sup>.**

COMPOUND	CAS No.	264 H	288 H	336 H
Formaldehyde	50-00-0	1.5	1.0	1.6
TVOC	-	49.6	42.1	45.2

\*BB – Below Blank

Individual emitted VOCs identified above the lower limits of quantitation are listed in Table 7; VOCs which are listed on chemical of concern lists or have CRELs are indicated.

The measured chamber concentrations and corresponding emission factors of identified individual VOCs and TVOCs are listed in Table 8.

In Tables 6, 8 and 9, emission factors were calculated using equation 3.1 in CDPH Standard Method V1.2:

$$EF_{Ai} = \frac{Q \times (C_{it} - C_{io})}{A_c}$$

The inlet flow rate,  $Q$  ( $m^3 h^{-1}$ ), is the measured flow rate of air into the chamber. The chamber concentration,  $C_{it}$  ( $\mu g m^{-3}$ ), is the concentration of a target VOC<sub>i</sub>, formaldehyde and other carbonyl compounds measured at time  $t$ . The chamber background concentration,  $C_{io}$  ( $\mu g m^{-3}$ ), is the corresponding concentration measured with the chamber operating without a test specimen. The exposed projected surface area of the test specimen in the chamber,  $A_c$  ( $m^2$ ), is determined from the measurements made at the time of specimen preparation.

**Table 5: VOCs detected above lower limits of quantitation in air samples at 336 hours.**

VOC	CAS No.	SURROGATE <sup>1</sup>	CREL <sup>2</sup> ( $\mu g m^{-3}$ )	CARB TAC <sup>3</sup>	PROP 65 LIST <sup>4</sup>
Formaldehyde	50-00-0		9	Yes	Yes
Acetaldehyde	75-07-0		140	Yes	Yes

<sup>1</sup>Indicates which non-listed VOCs were quantified using surrogate compounds, all other compounds were quantified using pure compounds.

<sup>2</sup>Chronic Reference Exposure Level (CREL) as defined by California Office of Environmental Health Hazard Assessment.

<sup>3</sup>Substance is listed on California Air Resource Board's (CARB) Toxic Air Contaminant (TAC) identification list.

<sup>4</sup>Substance known to the state of California to cause cancer or reproductive toxicity according to California's Safe Drinking Water and Toxic Enforcement Act of 1986 (Proposition 65).

**Table 6: Measured chamber concentrations and corresponding emission factors of individual VOCs listed in Table 4-1 of CDPH 01350 V1.2. at 336 hours.**

VOC	CAS No.	CHAMBER CONCENTRATION ( $\mu\text{g m}^{-3}$ )	EMISSION FACTOR ( $\mu\text{g m}^{-2} \text{h}^{-1}$ )
Formaldehyde	50-00-0	1.7	1.6
Acetaldehyde	75-07-0	25.6	42.7
Vinyl acetate	108-05-4	< 0.4	< 0.7
Epichlorohydrin	106-89-8	< 0.2	< 0.4
Ethanol, 2-methoxy-, acetate	110-49-6	< 0.3	< 0.6
Isopropyl Alcohol	67-63-0	< 0.2	< 0.3
Ethene, 1,1-dichloro-	75-35-4	< 0.2	< 0.3
Methylene chloride	75-09-2	< 0.3	< 0.5
Carbon disulfide	75-15-0	< 0.5	< 1
Methyl tert-butyl ether	1634-04-4	< 0.5	< 0.9
n-Hexane	110-54-3	< 0.3	< 0.5
Trichloromethane (Chloroform)	67-66-3	< 0.3	< 0.5
Ethanol, 2-methoxy-	109-86-4	< 0.4	< 0.7
Ethane, 1,1,1-trichloro-	71-55-6	< 0.2	< 0.3
Benzene	71-43-2	< 0.3	< 0.5
Carbon Tetrachloride	56-23-5	< 0.2	< 0.4
2-Propanol, 1-methoxy-	107-98-2	< 0.2	< 0.4
Ethylene glycol	107-21-1	< 8	< 15.1
Trichloroethylene	79-01-6	< 0.2	< 0.3
1,4-Dioxane	123-91-1	< 0.2	< 0.3
Ethanol, 2-ethoxy-	110-80-5	< 0.4	< 0.8
Toluene	108-88-3	< 0.2	< 0.4
Formamide, N,N-dimethyl-	68-12-2	< 0.4	< 0.8
Tetrachloroethylene	127-18-4	< 0.2	< 0.3
Benzene, chloro-	108-90-7	< 0.2	< 0.3
Ethylbenzene	100-41-4	< 0.2	< 0.3
Xylene (-m, -p, & -o)	108-38-3, 95-47-6, 106-42-3	< 0.6	< 1.2
Styrene	100-42-5	< 0.1	< 0.2
2-Ethoxyethyl acetate	111-15-9	< 0.5	< 0.9
Phenol	108-95-2	< 0.5	< 1
Benzene, 1,4-dichloro-	106-46-7	< 0.1	< 0.2
Isophorone	78-59-1	< 0.2	< 0.3
Naphthalene	91-20-3	< 0.2	< 0.4



**Table 7: Measured chamber concentrations and corresponding emission factors of identified individual VOCs and TVOC at 336 hours.**

VOC	CAS No.	CHAMBER CONCENTRATION ( $\mu\text{g m}^{-3}$ )	EMISSION FACTOR ( $\mu\text{g m}^{-2} \text{h}^{-1}$ )
TVOC	-	28.0	45.2

**Exposure Scenario Modeling and Evaluation:**

Estimated building concentrations for the private office and school classroom scenarios were calculated using equation 3.2a of CDPH Standard Method V1.2:

$$C_{Bi} = \frac{EF_{Ai} \times A_B}{Q_B}$$

The area specific emission rate  $EF_A$  at 336 hours (14 days) total exposure time is multiplied by the ratio of the exposed surface area of the installed material in the building,  $A_B$  ( $\text{m}^2$ ), to the flow rate of outside ventilation air,  $Q_B$  ( $\text{m}^3 \text{h}^{-1}$ ).

The modeling parameters used for private office and school classroom scenarios are listed in Table 10.

The modeled concentrations of identified individual VOCs for private office and school classroom scenarios are listed in Tables 11 & 12. Whether the modeled concentrations meet the maximum allowable concentration requirements specified in Table 4.1 of CDPH Standard Method V1.2 are also indicated.

**Table 8: Standard modeling parameters for wallcovering.**

PARAMETER	SYMBOL	VALUE	UNITS
Exposed Surface Area Installed in <i>Private Office (PO)</i>	$A_B$	33.4	$\text{m}^2$
Air flow rate of <i>Private Office (PO)</i>	$Q_B$	20.7	$\text{m}^3 \text{h}^{-1}$
Exposed Surface Area Installed in <i>Classroom (SC)</i>	$A_B$	94.6	$\text{m}^2$
Air flow rate of <i>Classroom (SC)</i>	$Q_B$	191	$\text{m}^3 \text{h}^{-1}$

Table 9: Projected concentrations of individual VOCs specified in Table 4-1 of CDPH 01350 V1.2.

VOC	CAS NO.	PROJECTED CONCENTRATION ( $\mu\text{g m}^{-3}$ )		CONC. LIMIT ( $\mu\text{g m}^{-3}$ )	RESULT Pass (P) /Fail (F)	
		PO	SC		PO	SC
Formaldehyde	50-00-0	2.6	0.8	9	P	P
Acetaldehyde	75-07-0	68.8	21.1	70	P	P
Vinyl acetate	108-05-4	< 1.2	< 0.4	100	P	P
Epichlorohydrin	106-89-8	< 0.6	< 0.2	1.5	P	P
Ethanol, 2-methoxy-, acetate	110-49-6	< 0.9	< 0.3	45	P	P
Isopropyl Alcohol	67-63-0	< 0.6	< 0.2	3,500	P	P
Ethene, 1,1-dichloro-	75-35-4	< 0.5	< 0.2	35	P	P
Methylene chloride	75-09-2	< 0.9	< 0.3	200	P	P
Carbon disulfide	75-15-0	< 1.5	< 0.5	400	P	P
Methyl tert-butyl ether	1634-04-4	< 1.5	< 0.5	4,000	P	P
n-Hexane	110-54-3	< 0.8	< 0.3	3,500	P	P
Trichloromethane (Chloroform)	67-66-3	< 0.9	< 0.3	150	P	P
Ethanol, 2-methoxy-	109-86-4	< 1.2	< 0.4	30	P	P
Ethane, 1,1,1-trichloro-	71-55-6	< 0.6	< 0.2	500	P	P
Benzene	71-43-2	< 0.8	< 0.2	1.5	P	P
Carbon Tetrachloride	56-23-5	< 0.6	< 0.2	20	P	P
2-Propanol, 1-methoxy-	107-98-2	< 0.7	< 0.2	3,500	P	P
Ethylene glycol	107-21-1	< 24.4	< 7.5	200	P	P
Trichloroethylene	79-01-6	< 0.5	< 0.2	300	P	P
1,4-Dioxane	123-91-1	< 0.5	< 0.1	1,500	P	P
Ethanol, 2-ethoxy-	110-80-5	< 1.2	< 0.4	35	P	P
Toluene	108-88-3	< 0.6	< 0.2	150	P	P
Formamide, N,N-dimethyl-	68-12-2	< 1.2	< 0.4	40	P	P
Tetrachloroethylene	127-18-4	< 0.5	< 0.2	17.5	P	P
Benzene, chloro-	108-90-7	< 0.5	< 0.2	500	P	P
Ethylbenzene	100-41-4	< 0.6	< 0.2	1,000	P	P
Xylene (-m, -p, & -o)	108-38-3, 95-47-6, 106-42-3	< 1.9	< 0.6	350	P	P
Styrene	100-42-5	< 0.4	< 0.1	450	P	P
2-Ethoxyethyl acetate	111-15-9	< 1.5	< 0.5	150	P	P
Phenol	108-95-2	< 1.6	< 0.5	100	P	P
Benzene, 1,4-dichloro-	106-46-7	< 0.4	< 0.1	400	P	P
Isophorone	78-59-1	< 0.5	< 0.1	1,000	P	P
Naphthalene	91-20-3	< 0.7	< 0.2	4.5	P	P

Table 10: Projected concentrations of identified non-listed individual VOCs.

VOC	CAS NO.	PROJECTED CONCENTRATION ( $\mu\text{g m}^{-3}$ )		CONC. LIMIT ( $\mu\text{g m}^{-3}$ )	Result Pass (P) /Fail (F)	
		PO	SC		PO	SC
TVOC <sub>Toluene</sub>	-	73.0	22.4	-	-	-

**PHOTOGRAPHS:**



## SECTION 4

### FACILITIES AND EQUIPMENT:

#### GCMS

INSTRUMENTATION USED:	Markes TD-100 Thermal Desorption Agilent 7890A GC Agilent 5975C MS
COLUMN USED:	Agilent HP-Ultra 2 (GC)

#### HPLC

INSTRUMENTATION USED:	Agilent 1260 Infinity Series
COLUMN USED:	Poroshell 120 EC-C18

**SECTION 5**  
**CHAIN OF CUSTODY**

 <b>intertek</b> Total Quality. Assured.	<b>Ship To:</b>
	Attn: VOC Laboratory
	4700 Broadmoor SE
	Suite 200
	Kentwood, MI 49512
Phone: 616-656-7401	

<b>Chain of Custody for Chemical Testing</b>	
Intertek Quotation Number:	Qu-00901125
Purchase Order (enter Company and Number):	ASI 65831

<b>Customer Information</b>	
Company:	ASI
Street Address:	123 Columbia Court N.
City/State/Postal code:	Chaska, MN 55318
Country:	USA
Contact Name & Title (for reporting):	Conor Cook, Resource Specialist
Contact Phone/Fax Numbers:	952-466-8261
Contact E-mail Address:	<a href="mailto:ccook@acousticalsurfaces.com">ccook@acousticalsurfaces.com</a>
Financially Responsible Co. :	Acoustical Surfaces Inc.

<b>Shipping Details</b>	
Packed & Shipped By:	
Shipping Date:	
Carrier/Airbill Number:	

<b>Requested Testing</b>	
Test to be performed:	CDPH 01350 V1.2

<b>Manufacturer Information (If Different)</b>	
Company:	
City/State/Country:	
Contact Name/Title:	
Phone Number/E-mail Address:	

<b>Customer Request for Certification</b>	
ETL Environmental VOC™ Certification:	<input type="checkbox"/> YES
ETL Environmental VOC+™ Certification:	<input checked="" type="checkbox"/> YES
SCS's Indoor Advantage™ Certification:	<input type="checkbox"/> YES
SCS's Indoor Advantage™ Gold Certification:	<input type="checkbox"/> YES
SCS's FloorScore® Certification:	<input type="checkbox"/> YES

<b>Special Customer Instructions</b>	

<b>Sample Details</b>	
Product Commercial Name*:	See below
Product Commercial Part No.(if not part of the name)*:	Cementitious Wood Fiber Acoustic Board
Manufacturer Sample Tracking ID:	01350V12-1
Date Manufactured*:	
Product Category & Use*:	Acoustical Panel for absorption
Sample Construction Materials*:	Wood and Cement
Plant Name & Location*:	
Collection Location within Plant:	
Date & Time Collected* :	
Number of Sample Pieces*:	4
Sample Collected by*:	
Phone/Fax Numbers*:	
E-mail Address*:	

<b>Customer Authorizes Laboratory to Submit Copies of Test Reports To:</b>	
Contact:	
Email Address:	
Organization:	
Contact:	
Email Address:	
Organization:	

<b>Intertek Use Only</b>	
Condition of Shipping Package:	Good
Condition of Sample:	Good
Sample ID:	GRR1809270014
GIN:	G103632425

<b>Sample Handling*</b>				
	<b>Printed Name*</b>	<b>Signature*</b>	<b>Date*</b>	<b>Company*</b>
Relinquished By:				
Received by:	Amanda Tonger	Amanda Tonger	10/01/2018	Intertek